

STABLE CRETE TECHNICAL DATA BULLETIN Last updated > 09.02.2003

PRODUCT DESCRIPTION

PRODUCT	StableCrete™
TYPE	Water Soluble Liquid (Polymerized Polyester Polymer)
RECOMMENDED USES	StableCrete™ permanently waterproofs and preserves concrete, brick, stucco and all masonry surfaces. Increases concrete compressive strength, seals against staining, neutralizes alkali, increases concrete tensile strength, provides problem-free bond for paint and floor coverings, prevents curing cracks and dusting, prevents saponification, retards evaporation, acid resistivity. Inside or outside, on new or old concrete.
COLORS	Translucent
TINTING	Quality Control Red Dye Optional
SHEEN	Non-Film Forming
SOLIDS BY WEIGHT	4.67%
VISCOSITY	Same as Water

STABLE CRETE TECHNICAL DATA BULLETIN

APPLICATION DATA

SURFACE PREPARATION	Remove all dirt, dust, oil, grease, asphalt, foreign matter or parting compounds. For freshly placed concrete, complete finishing operations and allow visible surface water to disappear. Surface must be able to bear foot traffic without marring or damaging the concrete. For newly cured bare concrete perform after construction clean up, level any areas gouged by trades and follow-up general clean-up instructions. For aged concrete, mechanically remove aged membranes; restore surface soundness by patching, grouting and crack filling. For vertical work, after form stripping, repair and refine surface, remove parting compound remnants. If a concrete cleaner is used, the area should be thoroughly washed to restore natural ph to the surface prior to application of StableCrete. Test for water absorption should be conducted on aged structures to insure absorption into the host material.
MIXING DIRECTIONS	N/A
APPLICATION METHODS	Spray application for best results. Also brush roller, squeegee or hand sprayer.
APPLICATION EQUIPMENT	Brush, airless sprayer, roller, squeegee or low pressure sprayer (Hudson Type Max psi 20 lbs.)
THINNING	None
DRYING TIME	StableCrete penetrates in approximately ½ to 1 hour per application, influenced somewhat by temperature, humidity and job conditions. Application must penetrate thoroughly before proceeding. Allow 24 hours before subjecting to heavy traffic. Allow 48 hours prior to painting.
SPREADING RATE	200 square feet per gallon on horizontal surfaces.
RECOMMENDED APPLICATION PRECAUTIONS	Vertical and shotcrete surfaces may require additional product due to run off or aggressive absorption. Spray application may be back-rolled to insure proper surface saturation, dwell time and penetration. Application temperatures greater than 80 degrees F (27C) or low humidity may require additional StableCrete. Do not apply Stable Crete to a frozen host material. Water used to cool a surface prior to applications to be removed. Brush out puddles and runs immediately. Do not allow ponded material to dry on the surface. StableCrete must remain in contact with the host surface in order to be absorbed into the concrete matrix.
CLEAN-UP	Warm, soapy water.

STABLE CRETE TECHNICAL DATA BULLETIN

LIMITATIONS

APPLICATION LIMITATIONS	Winter placements using temporary heat sources, such as torpedo heaters may require additional StableCrete. Protect StableCrete from freezing. In the event of a freeze/thaw, stir or agitate to uniformity before using. If separation is persistent, discard StableCrete. Applications under high humidity conditions may produce a slippery film. This may be removed with clean water and a stiff bristled broom. Before applying adhesives, wash surface with StableCrete Degreaser/Cleaner and allow to thoroughly dry. A test application is mandatory. For subsequent coating applications, perform proper surface preparation and consult the coatings manufacturer for more instructions. Make certain the most current version of this data guide is being used (call Customer Service to verify the most current version.) Proper application is the responsibility of the user. Field visits by Conselcor are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job site.
PACKAGING	Available in 5 gallon pail (18.93 L), 55 gallon drum (208L). Shelf life is typically 1 year when stored in unopened container under normal conditions. Do not allow to freeze in the container; do not store below 35 degrees F (1.7C).
WEIGHT BY GALLON	8.7 lbs + or - 0.2 lb
FLASH POINT	None
AVAILABILITY	StableCrete is available from Conselcor, 520 East Eau Gallie Boulevard, Indian Harbor Beach, Florida 32937 (321) 779-4478 Or order online at www.conselcor.com

STABLE CRETE TECHNICAL DATA BULLETIN

PACKAGING, SAFETY PRECAUTIONS

FIRST AID	If swallowed, do not induce vomiting. In case of skin contact, flush immediately with plenty of water followed by washing with soap and water. In case of eye contact, flush eyes immediately with plenty of water for at least 15 minutes. If affected by inhalation of vapors or spray mist, remove to fresh air. Apply artificial respiration and other support measures as required. If ingested, any type of overexposure or symptoms of overexposure occur during or following the use of this product, contact a Poison Control Center Emergency Room or physician immediately (have label information available). Keep out of reach of children. Emergency Medical or Spill Control Information (304) 843-1300.
IMPORTANT:	Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Spraying of any material can be hazardous. Wear respirator, eye protection and protective clothing.
MATERIAL SAFETY DATA	Material Safety Data Sheets for StableCrete products are available through Conselcor, Inc.
TESTING	Water porosity and acid reactivity test may be performed at any time by Conselcor or its agents prior to insurance of warranty.

15 Year Limited Warranty The manufacturer warrants that concrete treated with StableCrete will retain the waterproofing effect for a period of 15 years from the date of application, provided that the concrete has not been abraded away and that the owner gives Conselcor, Inc. written notice by certified mail of any claim within thirty days of the discovery of leaking. In the event the treated concrete loses the waterproofing effect during the limited warranty period, the manufacturer will provide sufficient materials to restore the waterproofing effect to the areas on which it was lost. This agreement does not include or cover any loss of waterproofing effect due to improper surface preparation, improper application, the improper use of StableCrete, structural defects or movement, water penetration caused by cracks or joint area requiring caulking, sealants or repointing, failure of the building, any damage to the building or contents thereof or any leakage due to mechanical damage or abuse.

THE PARTIES AGREE THAT THE MANUFACTURER OF STABLECRETE AND CONSELCOR, INC.'S LIABILITY HEREUNDER TO RESTORE THE WATERPROOFING EFFECT TO THE AREA ON WHICH IT WAS LOST, WHICH LIABILITY SHALL NOT EXCEED THE MATERIAL VALUE OF THE STABLECRETE INVOICED FOR THE PROJECT.